

## PRODUCT DATA

## PEGATEX NEW

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

info@mathysdirect.co.uk  
www.mathysdirect.co.uk

### DESCRIPTION

Latex paint for interior and exterior protection

### MAIN PROPERTIES

Mat appearance, easy cleanability, easy to apply, good hiding

### RECOMMENDED USES

Inner walls: plaster, rendering, panels fibre cement, Gyproc.

Exterior walls: bricks, all kinds of construction materials excepted new ones less than 2 years old.

### TECHNICAL DATA

Appearance:	Mat 2 (°60)
Colour:	White and Mathymix
Density:	+/- 1.4 g/cm <sup>3</sup>
Solids Content:	In volume: +/- 38 % In weight: +/- 55 %
Recommended film thickness:	Wet film: 100 µm (10 m <sup>2</sup> /l) Dry film: 37 µm (10 m <sup>2</sup> /l)
Flashpoint:	Not flammable
VOC-content:	20 g/l max.
Ready to use mixture:	29,8 g/l max.
Category:	A/a
EU Limit values:	75 g/l (2007) / 30 g/l (2010)

### Drying times 20°C/50% r.h.

To touch:	1 hour
To handle:	5 hours
To recoat:	After 4 hours
Full hardness	+/- 1 day

### Coverage

Theoretical: 8-10 m<sup>2</sup>/l per layer

Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

### SURFACE PREPARATION

Application on not alkaline substrates in good state.

Interior: porous surfaces to prime with Pegafix or with a first coat diluted with 10% water.

Exterior: Not painted substrates to prime with Pegafix.

### DIRECTION FOR USE

Before application, stir the product till complete homogenous.

### APPLICATION & THINNING

Brush: Do not dilute

Roller: Do not dilute

Air-atomised spray: If necessary, dilute with water

## PRODUCT DATA

## PEGATEX NEW

Airless spray: If necessary, dilute with water.  
Nozzle: 013/ Pressure: 180 bar.

Cleanup: Water

### APPLICATION CONDITIONS

Minimum 5°C en maximum 80 % RH

### SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

### SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

**Andrews Coatings Ltd**  
Carver Building  
Littles Lane  
Wolverhampton  
West Midlands  
WV1 1JY

**Tel. 01902 429190**

[info@mathysdirect.co.uk](mailto:info@mathysdirect.co.uk)  
[www.mathysdirect.co.uk](http://www.mathysdirect.co.uk)