

PRODUCT DATA

PARACEM DECO SATIN

DESCRIPTION

Waterborne acrylic paint for high-quality indoor works.

MAIN PROPERTIES

Excellent flow - excellent mechanical resistance against rubbing - smooth satin aspect - closed coating structure - washable - high covering power - high solids content – tendency not to overlap.

RECOMMENDED USES

Decorative and satin finishing for indoor walls and ceilings.
Applicable on most substrates (plaster, bricks, concrete, etc.) as well on glass fibre.

TECHNICAL DATA

Appearance:	Satin gloss (gloss 60°: 25 - 30% / 85°: 45 - 50%)
Colour:	White + Mathymix / ColourShop
Density:	1,32 - 1,36 g/cm ³ (white)
Solids Content:	In volume: 43 ± 1% (white) In weight: 58 ± 1% (white)
Recommended film thickness:	Wet film: ± 140 micron (consumption: 7 m ² /l) Dry film: ± 60 micron (consumption: 7 m ² /l)
Flashpoint:	Not flammable
VOC-content:	30 g/l max.
Ready-for-use mixture:	30 g/l max.
Category:	A/b
EU Limit values:	150 g/l (2007) / 100 g/l (2010)

Drying times 20°C/50% r.h.

To touch:	1 hour
To recoat:	2 hours
Full hardness:	± 2 days

Coverage

Theoretical:	7 - 10 m ² /l per coat
Practical:	Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

SURFACE PREPARATION

Old cleaned layers in good condition and light porous substrates can be recoated directly with Paracem Deco Satin.

Very porous substrates, smooth plaster and water-resistant plasterboard are to be impregnated first with Pegafix.

Nicotine stains must be isolated first with Pegaprim Isofix, Pegamat Aqua or Pegamat RL.

Old damp spots must be isolated with Pegamat RL or Pegaprim Isofix.

Unpainted woodwork must be treated appropriately first and a priming coat must be applied (e.g. Fassiprim or Pegaprim Xpress).

Metal objects without rust spots are to be pre-treated with Pegalink, Pegaprim Xpress or Galvaprim.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

Rust-Oleum Netherlands B.V.
Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S
11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.
Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu

PRODUCT DATA

PARACEM DECO SATIN

APPLICATION & THINNING

- Brush: Apply undiluted.
- Roller: Apply undiluted.
- Air-atomised spray: If necessary dilute with water.
- Airless spray: Nozzle: 013 - 019 / Pressure: 160 - 200 bars.
- Cleanup: Water.

APPLICATION CONDITIONS

> 5°C, < 80% R.H.

REMARK

In case of application on patterned vinyl wallpaper, Pegaprim Isofix should be used to block plasticizers migration and limit tacking effect.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info@rust-oleum.eu
www.rust-oleum.eu

N.V. Martin Mathys S.A.

Kolenbergstraat 23
3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)1 30 40 00 44
F +33 (0)1 30 40 99 80
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Rotterdam House
116 Quayside
Newcastle
NE1 3DY
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info@rust-oleum.eu
www.rust-oleum.eu