

PRODUCT DATA

FAIRTEX

DESCRIPTION

Waterbased matt acrylic dispersed paint for indoor walls and ceilings.

MAIN PROPERTIES

Easy and completely spatter-free roller application - even flat finish without overlaps - covers perfectly in 2 coats on most kinds of porous and not porous substrates without gloss differences - nearly odourless - high whiteness degree.

RECOMMENDED USES

Inner decoration on most common substrates such as plaster, bricks and concrete. Also old paint coats in good condition and most wallpaper can be recoated with Fairtex.

TECHNICAL DATA

| | |
|-----------------------------|---|
| Appearance: | Matt (gloss 60°: 2%) |
| Colour: | White |
| Density: | 1,38 - 1,41 g/cm ³ |
| Solids Content: | In volume: 28 - 32% In weight: 48 - 51% |
| Recommended film thickness: | Wet film: ± 140 micron (cons.: 7 m ² /l) Dry film: ± 45 micron (cons.: 7 m ² /l) |
| Flashpoint: | Not flammable |
| Sanding resistance: | > 5.000 cycles (DIN 53778) |
| VOC-content: | 30 g/l max. |
| Ready-for-use mixture: | 30 g/l max. |
| Category: | A/a |
| EU Limit values: | 75 g/l (2007) / 30 g/l (2010) |

Drying times 20°C/50% r.h.

| | |
|----------------|----------------|
| To touch: | 30 minutes |
| To handle: | Not applicable |
| To recoat: | 3 hours |
| Full hardness: | ± 1 week |

Coverage

| | |
|--------------|--|
| Theoretical: | 6 - 8 m ² /l |
| Practical: | Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. |

SURFACE PREPARATION

Always work on a dry and stable substrate. On porous substrates, no specific pre-treatment is required in most cases. Slightly chalking substrates or new plaster should first be impregnated with Pegafix. Damp substrates or nicotine stains should be isolated with Pegamat.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

APPLICATION & THINNING

| | |
|---------------------|------------------|
| Brush: | Apply undiluted. |
| Roller: | Apply undiluted. |
| Air-atomised spray: | Not recommended. |

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA

FAIRTEX

Airless spray: If necessary, dilute with 2 - 5% of water.
Nozzle: 016 - 018 / Pressure: 200 bars.

Cleanup: Water.

APPLICATION CONDITIONS

Apply at a temperature of min. 5°C and a R.H. of max. 80%.

SAFETY

Consult Safety Data Sheet and Safety Information printed on the can.

SHELLIFE / STORAGE CONDITIONS

2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com